



CRYSTAL ADMIX HD

OVERVIEW

Crystal Admix HD is a next generation crystalline admix designed to enhance concrete by effectively waterproofing the concrete, dramatically increasing strength and reducing the shrinkage cracks. Crystal Admix HD often eliminates the need for super plasticizers by providing high plastic qualities and abilities as part of its unique crystalline waterproofing abilities. It is a cost-effective solution to membrane systems while increasing concrete's durability. Crystal Admix HD is added to fresh concrete easily at the batch plant or directly into ready mix trucks. It works to continuously prevent moisture from penetrating through the concrete by creating a catalytic chemical reaction within the pores and capillaries to enhance the hydration process of the cement component within the concrete. The enhanced hydration process not only provides waterproofing characteristics to the concrete, it also allows for an increased ability to self-heal micro cracking upon the presence of moisture.

FEATURES

- Is a permanent, one time only application for the life of the concrete
- Is user friendly and easy to apply
- Is added directly to the fresh concrete during mixing or premixed with cement powder

ADVANTAGES

- Will reduce shrinkage cracks by up to 60%
- Will reduce water demand by 10 to 16%
- Will eliminate the use of a waterproofing subtrade
- Will continually improve waterproofing benefits with time
- Will assist concrete in the hydration process
- Will protect against water penetration through microcracks by autogenously healing future micro-cracking
- Will reactivate the waterproofing mechanism should water be present in the future
- Will increase the durability and sustainability of the concrete
- Will protect against cracking and spalling
- Will stop water penetration into the concrete
- Will provide the best quality to cost ratio in the industry
- Will eliminate the need for any other waterproofing system

BENEFITS

- Protection of reinforcing steel against chemical attack
- Protection against deterioration of the concrete due to waterborne chemical attack
- Protection against deterioration of the concrete due to AARI ASR
- Protection against deterioration of the concrete due to cast in contaminants
- Protection against deterioration of the concrete due to carbonization
- Protection against heavy hydrostatic pressure
- Protection against deterioration due to freeze/thaw environments

TECHNIGAL DATA SHEET

RECOMMENDED FOR

- Tunnels and subway systems
- Parking garages Sewage and water
- treatment plants
- All below grade concrete foundations
- Water towers and
- Swimming pools
- Rooftops
- Dry vaults / Basements
- Marine structures
- Pipes
 - Bridge decks
- water reservoirs
- Concrete walls and floor

APPLICATION

Crystal Admix HD is a dry powder that may be added directly to the wet mix concrete during batching or added directly to the ready-mix truck prior to arrival at the site or at the site. The dosage rate is 1 kg per 100kg of cement (see Dosage). Reduce the water component by 10 to 16%, to offset increased slump and workability. Mix for 10 minutes at high speed before placing to insure a thorough mix. Should a superplasticizer be required, add it after the addition of the Crystal Admix HD. Do not add water to the mix to increase slump. Place the concrete within 45 minutes to utilize the maximum benefits of flow and placement values. Avoid early finishing and over trowelling.

NOTES

- Crystal Admix HD may delay initial and final set times.
- Crystal Admix HD is free of oils, stearates, chlorides, sodium and silicate-based materials.
- Crystal Admix HD may not always be compatible with polycarboxylate plasticizers and should be batch tested before use with them.

PHYSICAL PROPERTIES

| Color | grayish brown | |
|-------------------|-----------------|--|
| Appearance | granular powder | |
| Max Particle Size | max 0.297 | |
| Solids | 100% | |
| Bulk density | 1.0 | |
| РН | 13 | |

CURING

Standard concrete wet curing procedures.

DOSAGE

Dosage is approximately 1% of cement content.

NOTE

- Crystal Admix HD is measured to the cement and cementitious components such as fly ash and silica fume only and is not measured to the full concrete design.
- The dosage rate may be reduced subject to the type of pozzolanic materials used and design mix.

PRECAUTIONS

This material becomes caustic when mixed with water or perspiration. A void contact with skin or eyes. In case of skin contact, wash with soap and water. Flush eyes immediately with warm water for several minutes. If ingested, do not induce vomiting. If victim is alert, give two glasses of water. Avoid breathing dust. Wear long sleeves, eye goggles and a dust mask. See the material safety data sheet for this product.

PACKAGING

18kg buckets





DEGLARATION OF PERFORMANCE

| | laration of Performan Annex III of the Regulation | |
|---|---|-------------------------------------|
| | code of the product-type: | (EO) NO. 574/2014 |
| | Crystal Admix HD | |
| | erystar Admix HE | |
| 2. Intended use/es: | | |
| | JIREMENTS FOR WATER RES | |
| |) according table 9 of the standa | ard EN 934-2:2010+A1:2012 |
| 3. Manufacturer: | Concrete Agua Guard Lta | l l |
| | Concrete Aqua Guard Lto Teelin Rd, Carrick Co. Doneg | |
| | reenin ku, carriek co. Doneg | 501, |
| | Ireland | |
| | | |
| | | |
| Authorised representative | | |
| | Not Relevant | |
| 5. System/s of AVCP: | | |
| | System 2+ | |
| 6a. Harmonised standard: | | |
| | EN 934-2 | |
| Notified body/ies: | | |
| | | |
| | | |
| porformed the initial increati | Aw CERTIFICACIÓN | nd of factory production control ar |
| | | f factory production control under |
| | ertificate of conformity of the Fa | |
| | 1170/CPR/ER.03608 | , |
| 7. Declared performance/s | 1 | 1 |
| Essential requirement | Performance | Harmonized technical |
| Chloride ion content | - 0.19/ | specification EN 480-10 |
| Alkali content | ≤ 0,1% ≤ 17% | EN 480-10 |
| Aikail content | Contains only approved | |
| Corrosion behavior | substances according to EN | EN 480-14 |
| 0 | 934-1:2008 Annex A1 | |
| Compressive strength | ≥ 85% above reference | EN 12390-3:2009/AC:2011 |
| at 7 days Air content | concrete ≤2% above | |
| in the fresh concrete | reference concrete | EN 12350-7:2010 |
| Capillary absorption | At 7 days (≤50%) | |
| (g/mm²) | At 28 days (≤60%) | EN 480-5:2006 |
| | NPD | See material safety data sheet |

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

adraig last

Padriag Carr, TECHNICAL DIRECTOR In Donegal, on June 26, 2018